

Description

Lexan* 9600 sheet offers all the benefits of standard, transparent polycarbonate sheet - excellent impact resistance, good stiffness and strength, high optical quality, excellent formability, relatively light weight - but it has significantly better flammability characteristics, making it suitable for a wide variety of applications in the transportation, electrical and electronic industries.

Typical Property Values ♦

Property	Test Method	Unit	Value
Physical			
Density	ISO 1183	g/cm ³	1.25
Water absorption, equilibrium, 23°C	ISO 62	%	0.35
Rockwell Hardness	ASTM D785		M74
Mechanical			
Tensile Strength, yield	ISO 527	MPa	60
Tensile Strength, break	ISO 527	MPa	70
Tensile modulus	ISO 527	MPa	2350
Tensile elongation, break	ISO 527	%	120
Flexural strength, yield	ISO 178	Mpa	90
Flexural modulus	ISO 178	MPa	2300
Izod notched impact, 23°C	ISO 180/1A	kJ/m ²	65
Gardner impact, 23°C	ASTM D3029	J	>40
-30°C		J	>40
Taber Abrasion, CS17, 1000g, 1000cycles	ASTM D1242	mg	9
Thermal			
Vicat Softening Temp, Rate B /120	ISO 306	°C	145
DTUL, 0.45 MPa	ISO 75/Be	°C	138
Thermal Conductivity	ASTM C 177	W/m°C	0.20
Mold Shrinkage	ISO 527	%	0.6-0.8
Coefficient of Thermal Expansion	ASTM D696	1/°C	7x10 ⁻⁵
Electrical			
Dielectric Strength	IEC 60243	kV/mm	17
Dielectric Constant, 60Hz			3.17
1 MHz			2.96
Dissipation Factor 50Hz	ASTM D150		0.001
1MHz			0.01
Volume Resistivity, 23°C	IEC 60093	Ohm.cm	>10 ¹⁵

♦ These property values have been derived from Lexan* resin data for the material used to produce this sheet product.

* Trademarks of SABIC Innovative Plastics IP BV

Processing

Lexan* 9600 sheet is ideally suited to thermoforming. It offers high, deep draw ratios, equal wall thickness distribution, and it can be formed into complex shapes using standard thermoforming equipment. Sandwich type heating systems give the best results. Lexan 9600 sheet has a forming temperature range of 185 - 205°C. When forming, a draft angle of at least 3° should be allowed, and post mold shrinkage of 0.6 - 0.8% taken into account.

Pre-drying

It is important to ensure that Lexan 9600 sheets are free of moisture prior to thermoforming. A hot air circulating oven set at 120°C is recommended. Pre-drying times vary from 3-24 hours, depending on sheet thickness.

Assembling

Parts made from Lexan 9600 sheet can be assembled with plastics, metals, rubber and other materials using many types of adhesive bonding, welding and mechanical fastening techniques. Since some of these materials can cause environmental stress cracking, please consult SABIC Innovative Plastics for advice on specific applications.

Painting

Lexan 9600 sheet is ideally suited for use with a wide variety of modern decoration techniques. A list of approved paint systems and suppliers is available on request.

Chemical Resistance

Lexan 9600 sheet has sufficient resistance to most mineral oils, greases, aliphatic hydrocarbons and acids under low or moderate stress levels. In applications where the Lexan 9600 sheet will come into contact with aggressive chemicals, specific (application related) testing is always advised. Effective painting systems can improve chemical resistance

Fire test performance

Lexan 9600 sheet has good fire performance against many national fire codes dependent on thickness and color; please check with the local sales office for details.



* Trademark of SABIC Innovative Plastics IP BV

Americas:
SABIC Innovative Plastics
Specialty Film & Sheet
One Plastics Avenue
Pittsfield, MA 01201
USA
Tel. (1) (413) 448 5400
Fax. (1) (413) 448 7506
Toll free: 1-800 451 3147

Europe:
SABIC Innovative Plastics
Specialty Film & Sheet
Plasticslaan 1
NL - 4612 PX Bergen op Zoom
The Netherlands
Tel. (31) (164) 292911
Fax. (31) (164) 293272

Pacific:
SABIC Innovative Plastics
Specialty Film & Sheet
1266 Nanjin Road (W)
Plaza 66, 17th Floor
200040 Shanghai, China
Tel. (86) 21 62881088
Fax. (86) 21 62880818

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of Sabic Holding Europe BV

* Trademark of SABIC Innovative Plastics IP BV